

# PITTWRAP<sup>®</sup> SS PRIMER

## Product Datasheet

# FOAMGLAS<sup>®</sup>

Pittsburgh Corning

## 1. Description and Area of Application

PITTWRAP<sup>®</sup> SS Primer is specially formulated to promote adhesion of self-sealing, bituminous PITTWRAP<sup>®</sup> jacketing when the laps are slightly dusty or the temperature at application is between -7 and 10 °C (20 and 50 °F).

## 2. Field Application

Always read and understand information contained within product datasheets and safety datasheets before attempting to use this product. If you have questions regarding fitness of use of this product for a particular application, consult Pittsburgh Corning.

Apply a thin coat of primer to the bituminous side of the jacketing lap with a brush or swab. Allow the solvent to evaporate for a few minutes before seal is made. Press lap and roll completed joint with a hard roller such as a wallpaper seam roller.

Check for unsealed areas along the seam and repress or reseal before back filling. Refer to specific self-sealing PITTWRAP<sup>®</sup> jacketing product data sheets for details of jacketing application.

## 3. Type of Delivery and Storage

- 3.8 L (1 gal) can. Approximate weight 4.5 kg (10 lb) per can.
- Store in a well-ventilated room away from ignition sources.
- Store closed containers between -15 °C and 35 °C (5 °F and 95 °F) for solvent based coatings and thinners.
- Ground all metal containers.

## 4. Coverage

- Determine the amount of primer needed by calculating the surface area to be coated. Using the surface area to estimate the amount of Hold Catalyst needed based on the coverage listed below.
- Hold Catalyst Coverage: 1.9 m<sup>2</sup> / L (75 ft<sup>2</sup> / gal)

Figures DO NOT include losses. Typically, adding 10% to coverage area will account for losses.



## 5. Typical Properties

PROPERTY <sup>A</sup>	METHOD	SI	ENGLISH
COLOR		Translucent White (liquid)	
SOLIDS CONTENT, VOLUME		~ 21%	
FLASH POINT	TCC	4 °C	40 °F
APPLICATION TEMPERATURE		15.5 ± 22.5 °C	60 ± 40 °F
REACTION TO FIRE			
WET			Flammable
DRY			Combustible
SOLVENT		Toluene	

<sup>A</sup> Properties subject to change. Consult Pittsburgh Corning.

## 6. Limitations

- It is used only to assist in making a bond.
- Use only on the bituminous side of the jacketing.
- Solvent may attack organic foams.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning Corporation has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Pittsburgh Corning products. In no event shall Pittsburgh Corning be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning Corporation provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.

**Pittsburgh Corning Corporation** To contact by phone or email:

**Global Industry Headquarters**  
**800 Presque Isle Drive**  
**Pittsburgh, PA 15239 USA**

For web-based Sales and Technical  
 Service inquiries, please visit  
[www.foamglas.com](http://www.foamglas.com).

**Industrial & Commercial Sales**

**Americas**

+1 724 327 6100

+1 800 545 5001

**Asia-Pacific**

Singapore: + 65 9635 9184

China: +86 (0) 21 6140 8002

Japan: + 81 50 7554 0248

**Europe, Middle East & Africa**

+32 13 661 721

**Technical Services**

**Americas & Asia Pacific**

+1 800 327 6126

Foamglastechnical@pghcorning.com

**Europe, Middle East & Africa**

+32 13 611 468

Industrytechnical@foamglas.com